

Michilene F8100GF30-03

Polypropylene Homopolymer

API Polymers, Inc.

Message:

Michilene F8100GF30-03 is a polypropylene homopolymer (PP Homopoly) product, which contains a 30% glass fiber reinforced material. It is available in North America. The main characteristics are: homopolymer.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Homopolymer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	44.8	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus - Tangent	3450	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	135	°C	ASTM D648
1.8 MPa, not annealed	124	°C	ASTM D648
Additional Information			
Drying Generally Not Necessary.			
Injection	Nominal Value	Unit	
Drying Temperature	82.0	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	221	°C	
Middle Temperature	221	°C	
Front Temperature	224	°C	
Nozzle Temperature	227	°C	
Processing (Melt) Temp	227	°C	
Mold Temperature	38.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

