

RTP 505 HB

Styrene Acrylonitrile
RTP Company

Message:
Glass Fiber - UL94 HB

General Information			
UL YellowCard	E84658-251612		
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.10 - 0.20	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	123		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10300	MPa	ASTM D638
Tensile Strength	117	MPa	ASTM D638
Tensile Elongation (Yield)	1.0 - 2.0	%	ASTM D638
Flexural Modulus	9650	MPa	ASTM D790
Flexural Strength	152	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	48	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	240	J/m	ASTM D4812
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Additional Information	Nominal Value	Unit	
Primary Additive	30	%	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	238 - 279	°C	
Mold Temperature	51.7 - 82.2	°C	
Injection Pressure	68.9 - 103	MPa	
Injection instructions			

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHEG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT