# Sanren Y200L (Premium-grade)

#### Polypropylene Homopolymer

SINOPEC Shanghai Petrochemical Co. Ltd.

#### Message:

The pellet product is colourless and in the shape of a cylinder with good mechanical performance, stress-fracture resistant, excellent chemical stability, as well as high resistance to ultra-violet

Scope of Application: Slit fibre for rope/string or knitting.

| General Information                   |  |                          |                 |
|---------------------------------------|--|--------------------------|-----------------|
| Features                              | High ESCR (Stress Cracking Resistance) |                          |                 |
|                                       | Homopolymer                            |                          |                 |
|                                       | Good UV resistance                     |                          |                 |
|                                       |  |                          |                 |
| Uses                                  | Rope                                   |                          |                 |
|                                       | Fiber                                  |                          |                 |
|                                       |  |                          |                 |
| Appearance                            | Colorless                              |                          |                 |
| Forms                                 | Particle                               |                          |                 |
| Processing Method                     | Extrusion                              |                          |                 |
| Physical                              | Nominal Value                          | Unit                     | Test Method     |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 |  |                          |                 |
| kg)                                   | 1.6 - 2.5                              | g/10 min                 | Internal method |
| Chlorine Content                      |  | %                        |                 |
| Ash Content                           |  | %                        |                 |
| Fish Eye                              |  |                          |                 |
| 400.0 μm                              | 0.00 - 20.0                            | pcs/1520 cm <sup>2</sup> |                 |
| 800.0 µm                              | 0.00 - 4.00                            | pcs/1520 cm <sup>2</sup> |                 |
| Isotacticity                          | > 95                                   | %                        |                 |
| Mechanical                            | Nominal Value                          | Unit                     | Test Method     |
| Tensile Strength (Yield)              | > 35.0                                 | MPa                      | ASTM D638       |
| Flexural Modulus                      | > 1400                                 | MPa                      | Internal method |
| Impact                                | Nominal Value                          | Unit                     | Test Method     |
| Unnotched Izod Impact (23°C)          | > 39                                   | J/m                      | Internal method |
| Thermal                               | Nominal Value                          | Unit                     | Test Method     |
| Vicat Softening Temperature           | > 154                                  | °C                       | Internal method |
| Optical                               | Nominal Value                          | Unit                     | Test Method     |
| Yellowness Index                      | < 4.0                                  | YI                       | Internal method |
| Additional Information                | Nominal Value                          | Unit                     |                 |
|                                       |  |                          |                 |

Cleanliness: 0-5 pieces/kg

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2