

Solef® 60512/0550 and 60512/0150

Polyvinylidene Fluoride

Solvay Specialty Polymers

Message:

Solef® 60512/0550 and Solef® 60512/0150 are PVDF grades compounded with PTFE for extrusion of anti-wear tapes.

General Information			
Features	Copolymer		
Uses	Tape		
Physical	Nominal Value	Unit	Test Method
Density	1.80 to 1.82	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	2.0 to 4.5	g/10 min	ASTM D1238
Water Absorption (23°C, 24 hr)	< 0.040	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (23°C, 1.50 mm)	1100 to 1350	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield, 23°C, 1.50 mm	30.0 to 40.0	MPa	
Break, 23°C, 1.50 mm	30.0 to 40.0	MPa	
Tensile Elongation ³			ASTM D638
Yield, 23°C, 1.50 mm	8.0 to 12	%	
Break, 23°C, 1.50 mm	50 to 300	%	
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.10 to 0.20		
vs. Itself - Static	0.050 to 0.20		
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-10 Wheel)	5.00 to 10.0	mg	ASTM D4060
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	170 to 174	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	144 to 148	°C	ASTM D3418
Crystallization Heat	38.0 to 48.0	J/g	ASTM D3417
Heat of Fusion - (80°C to end of melting)	41.0 to 50.0	J/g	ASTM D3417
NOTE			
1.	Type V, 1.0 mm/min		
2.	Type V, 50 mm/min		
3.	Type V, 50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

