

MARPOL® PET IV 76 WB

Polyethylene Terephthalate

Marco Polo International, Inc.

Message:

Features:

Good process ability

Low preform AA and

Excellent clarity / gloss in bottles

Typically used for: Still water application

Certifications:

PET MarPol IV 76 WB resin is considered safe for food-packaging applications based on compliance with FDA regulation 21 CFR Section 177.1630 & other similar food contact safety regulations.

General Information			
Features	Food Contact Acceptable		
	Good Processability		
	High Clarity		
	High Gloss		
Uses	Bottles		
Agency Ratings	FDA 21 CFR 177.1630		
Physical	Nominal Value	Unit	Test Method
Acetaldehyde	1.0	ppm	Internal Method
Color b - CIE	-3.00 to 0.00		Internal Method
Crystallinity	50	%	Internal Method
Intrinsic Viscosity	0.76	dl/g	Internal Method
Chips/Gram	72.0		Internal Method
Fines	100	ppm	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT