

TARFLON™ AZ1900T

Polycarbonate
Idemitsu Kosan Co., Ltd.

Message:
Transparency, Flame retardant

General Information			
UL YellowCard	E48268-240384		
UL File Number	E48268		
Appearance	Clear/Transparent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	5.00	cm ³ /10min	ISO 1133
Spiral Flow	48.0	cm	Internal Method
Molding Shrinkage	Internal Method		
Across Flow : 2.00 mm	0.50 to 0.70	%	
Flow : 2.00 mm	0.50 to 0.70	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.23	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness	ISO 2039-2		
M-Scale	50		
R-Scale	120		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	65.0	MPa	ISO 527-2
Nominal Tensile Strain at Break	70	%	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	65	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	140	°C	ISO 75-2/B
1.8 MPa, Unannealed	125	°C	ISO 75-2/A
CLTE - Flow	6.5E-5	cm/cm/°C	ISO 11359-2
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746
RTI Str	80.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method

Electric Strength	30	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	2.85		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance	85.0 to 89.0	%	ISO 13468-1
Additional Information	Nominal Value		
ISO Shortname	>PC<		
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	5.0 to 8.0	hr	
Rear Temperature	260 to 300	°C	
Middle Temperature	260 to 300	°C	
Front Temperature	260 to 300	°C	
Mold Temperature	80.0 to 120	°C	
NOTE			

1. 24h

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

