Spartech Polycom SCR7-7210

Polycarbonate

Spartech Polycom

Message:

Spartech SCR7-7210 is a high flow PC resin for injection molding. It is heat stabilized and lubricated for good processing characteristics. Polycarbonate resins span a wide range of physical properties that combine to make it one of the toughest, most versatile of all engineering thermoplastics. It is well known for its exceptional impact resistance, plus it has outstanding mechanical, electrical, and optical properties. A very versatile product for a wide variety of applications, Spartech SCR7-7210 is recommended for industrial, transportation, sporting goods and electrical/electronic applications.

General Information					
Additive	heat stabilizer Lubricant				
Features	Impact resistance, high				
	Workability, good				
	Good electrical performance				
	High liquidity				
	Thermal Stability				
	Thermal stability, good				
	Good toughness				
	Lubrication				
Uses	Electrical/Electronic Applications				
	Industrial application				
	Application in Automobile Field				
	Sporting goods				
Appearance	Available colors				
	Natural color				
Forms	Particle				
Processing Method	Injection molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.25	g/cm³	ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield, 23°C)	66.2	MPa	ASTM D638		
Flexural Modulus (23°C)	3450	MPa	ASTM D790		
Flexural Strength (23°C)	103	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (23°C)	110	J/m	ASTM D256		

Thermal	Nominal Value	Unit	Test Method		
Deflection Temperature Under Load (1.8					
MPa, Unannealed)	142	°C	ASTM D648		
Injection	Nominal Value	Unit			
Drying Temperature	121	°C			
Drying Time	3.0 - 4.0	hr			
Rear Temperature	266 - 277	°C			
Middle Temperature	271 - 282	°C			
Front Temperature	282 - 299	°C			
Nozzle Temperature	277 - 304	°C			
Processing (Melt) Temp	288 - 316	°C			
Mold Temperature	71.1 - 93.3	°C			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

