

Retpol® 1024/5 HS UV2

Polypropylene

PolyPacific Pty. Ltd.

Message:

Corton 1024/5 HS UV2 is a 20% talc filled polypropylene compound. It is a high flow injection moulding grade developed for rigid components requiring good mar resistance and high impact strength. It is stabilized to meet automotive heat ageing and weathering requirements.

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Additive	Heat Stabilizer		
	UV Stabilizer		
Features	Heat Stabilized		
	High Flow		
	High Impact Resistance		
	Scratch Resistant		
Uses	Automotive Applications		
	Automotive Interior Parts		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	17	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.00 mm)	1.1 to 1.3	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 3.00 mm)	90		ASTM D785
Durometer Hardness			ASTM D2240
Shore D, 3.00 mm	74		
Shore D, 15 sec, 3.00 mm	66		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.00 mm)	28.0	MPa	ASTM D638
Tensile Elongation ² (Break, 3.00 mm)	43	%	ASTM D638
Flexural Modulus (3.00 mm)	2400	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.00 mm)	42	J/m	ASTM D256
Unnotched Izod Impact (3.00 mm)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.00 mm)	116	°C	ASTM D648
CLTE - Flow (-30 to 30°C, 3.00 mm)	8.0E-5	cm/cm/°C	ASTM D696
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Regrind	10	%	
Processing (Melt) Temp	200 to 260	°C	
Mold Temperature	20.0 to 60.0	°C	
Injection Rate	Moderate-Fast		
NOTE			
1.	50 mm/min		
2.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

