

# Pyramid™ PEEK KD2530-NT

Polyetheretherketone

Polymics, Ltd.

## Message:

Pyramid™ PEEK KD2530-NT is a Polyetheretherketone (PEEK) product filled with 20% ptfе fiber. It is available in North America. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	PTFE Fiber,20% Filler by Weight		
Features	Lubricated		
Appearance	Grey		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm <sup>3</sup>	ASTM D792
Water Absorption (24 hr)	0.10	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	84		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3170	MPa	ASTM D638
Tensile Strength (Break)	79.3	MPa	ASTM D638
Tensile Elongation (Break)	15	%	ASTM D638
Flexural Modulus	3450	MPa	ASTM D790
Flexural Strength (Yield)	138	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.10		
vs. Itself - Static	0.10		
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	43	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	171	°C	ASTM D648
Glass Transition Temperature	143	°C	DSC
Melting Temperature	343	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

